CDI PRODUCTS®
A Michelin Group Company

Material Data Sheet
ARMORLENE® A200

COMPOUND: ARMORLENE® A200

POLYMER: Polytetrafluoroethylene (PTFE)

DESCRIPTION: Material per AMS3678/9, PTFE filled with inorganic pigment, brown in color.

Property	Test Method	Internal Specification Values	Typical Values	Units
Specific Gravity	ASTM D792	2.14 – 2.20	2.17	-
Hardness	ASTM D2240		60	SHORE-D
Tensile Strength at Break	ASTM D4894	4,500 (31.03) Minimum	5,500 (37.92)	PSI (MPa)
Elongation at Break	ASTM D4894	350 Minimum	400	%
Dimensional Stability (Samples air aged at 350 °F (177 °C) for 1 Hour)	AMS 3678 4.5.3.1	0.002 inch/inch, max, measured on circumference	0.0001	Inch/inch

REV. NONE – Initial Release, 10-02-2026 RSK

The descriptions, design, and performance information, and recommended uses for the products, tests and data described herein are based generally on our design and manufacturing experience, product testing in specific conditions, and industry standards. The foregoing information is for general guidance only and does not constitute a guaranty or warranty of design or warranty of performance. All warranties regarding the products described herein will be given in writing at the time of sale of such products. Each purchaser of such products must decide if the products are suitable to the intended use of such purchaser. Armorlene®, Arylast™, Arylex®, dures®, CDI Products®, CDI Energy Products®, Fibrex®, Hythane®, Paradyne®, Permeon®, OptiSeal®, OptiPak®, Tuff Breed®, and WSP Extreme® are registered trademarks of J.H. Fenner & Co. Limited or other members of Fenner Group Holdings Limited, the divisional parent company of CDI Products, LLC, or its corporate parents (including Compagnie Générale des Etablissements Michelin SCA).